

Fire retardant finish 04

For products:

KLETTOSTAR®-hook	Art. 15147
KLETTOSTAR®-loop	Art. 15244
KLETTOSTAR®-unbrushed loop (as counterpart to Klettoplast)	Art. 53248

Technical Data

Finish 04:

Flame retardant finish;
Meets the requirements of the vertical test method of FAR §25.853 (a) App. F, Part I, (a) (1) (ii) and DIN EN ISO 6941 as well as the smoke density and toxicity requirements of ABD 0031.

Shrinkage after washing at 40°C:


	Hook and Loop
Lengthwise	2.5 - 3.0 %
Widthwise	1.0 - 2.0 %

Fraying:

acc. to DIN 3415, part 2, para. 5.4 = mark 4

After washing the fastener is softer but this has no effect on the flame retardant properties.

Washing instruction:



Wash, dry-clean, iron and spin-dry only when fastener is closed!

All information in this document has been compiled carefully from the best knowledge gained by Gottlieb Binder GmbH & Co.KG from the framework of their quality management systems. It describes product from the aspect of composition and application but does not constitute any quality assurance. Besides it does not release the customer from their obligation to control received goods and to carry out initial product testing nor provide any justification for the pursuit of third party claims. In the legal sense, no quality safeguard is implied or given. The right is reserved to make technical alterations.